

06/16/98



Please type a plus sign (+) inside this box->/ + /

UTILITY	Atty Doc. No. <u>48101</u> Total Pages <u>34</u>
PATENT APPLICATION	FIRST NAMED INVENTOR OR APPLICATION IDENTIFIER
TRANSMITTAL	Stephan HUEFFER
	Express Mail Label No. _____

U.S. PTO

Application Elements

Address To: Assistant Commissioner for Patents
Box Patent Application
Washington, D.C. 20231

1. / X / Fee transmittal Form
(Submit an original, and a duplicate for fee processing)
2. / X / Specification Total Pages / /
(Preferred arrangement set for below)

Descriptive title of the Invention

Cross References to Related Application

Statement Regarding Fed. Sponsored R & D

Reference to Microfiche Appendix

Background of the Invention

Brief Summary of the Invention

Brief Description of the Drawings (if filed)

Detailed Description

Claim(s)

Abstract of the Disclosure

3. / Drawing(s)(35 USC 113) Total Sheets / /

4. / Oath or Declaration Total Pages / /

a. / Newly executed (original or copy)

b. / Copy from a prior application (37 CFR 1.63(d)
(For Continuation/Divisional with Box 17 completed)
Note Box 5 belowi. / DELETION OF INVENTOR(S)Signed statement attached deleting
inventor(s) named in the prior application
see 37 CFR 1.63(d)(2) and 1.33(b).

5. / Incorporation by reference (useable if Box 4b is checked)

The entire disclosure of the prior application, from which a
copy of the oath or declaration is supplied under Box 4b
is considered as being part of the disclosure of the accompanying
application and is hereby incorporated by reference therein.

6. / Microfiche Computer Program (Appendix)

7. / Nucleotide and/or Amino Acid Sequence Submission
(if applicable, all necessary)

a. / Computer Readable Copy

b. / Paper Copy (Identical to computer copy)

c. / Statement verifying identity of above copies

ACCOMPANYING APPLICATIONS PARTS

8. / Assignment Papers (cover sheet & document(s))

9. / 37 CFR 3.73(b) Statement / / Power of Attorney

10. / English Translation Document (if applicable)

11. / Information Disclosure / X / Copies of IDS Citations

12. / Preliminary Amendment

13. / X / Return Receipt Postcard (MPEP 503)

Should be specifically itemized)

14. / Small Entity / / Statement filed in prior application
Statements Status still proper and desired15. / Certified Copy of Priority Document(s)
(if foreign priority is claimed)16. / Other _____

17. If a Continuing Application, check appropriate box and supply the requisite information:

/ / Continuation / / Divisional / / Continuation-in part (CIP) of prior application No. _____

CORRESPONDENCE ADDRESS

/ / Customer Number or Bar code Label

or / / Correspondence address below

Insert Customer No. or Attach bar code label here

Name: Herbert B. Keil
KEIL & WEINKAUF

Address: 1101 Connecticut Ave., N.W.

City: Washington

State: D.C.

Zip Code 20036

Country: USA

Telephone: (202)659-0100

Fax: (202)659-0105

09097865 "061698


The filing fee has been calculated as shown below:

For:	Number Filed	Number Extra	SMALL/LARGE ENTITY	BASIC FEE \$395./\$790.
Basic Fee.....				\$ 790.00
Total Claims:	<u>14</u> -0 =	x	\$11./\$22. =	
Indep. Claims:	<u>2</u> -3 =	x	\$41./\$82. =	
[] Multiple Dependent Claim(s) presented:	\$135./270 =			
[] A check is enclosed for the filing fee.				\$ <u>790.00</u>

*If the difference is less than zero, enter "0".

- [X] A check for \$ ^{790.00}~~830.00~~ for the filing fee and assignment is enclosed
- [X] The Commissioner is hereby authorized to charge any other fee required, including the issue fee, in connection with the filing and prosecution of this application, and to the extent necessary, applicant(s) hereby petition for extension(s) of time under 37 CFR 1.136, to be charged to our Deposit Account 11-0345.

Respectfully submitted,
KEIL & WEINKAUF


Herbert B. Keil
Reg. No. 18,967

1101 Connecticut Ave., N.W
Washington, D.C. 20036
(202) 659-0100

09057865 "001648

Propylene polymers

5 The invention relates to propylene polymers containing a matrix
of a propylene homopolymer and a copolymer of propylene and other
alkenes, wherein, during the separation of the propylene polymers
according to tacticity and comonomer distribution of the polymer
chains, by first dissolving the propylene polymers in boiling
10 xylene, then cooling the solution at a cooling rate of 10°C/h to
25°C and thereafter, increasing the temperature, separating the
propylene polymers into fractions of different solubility, either
one or more of the conditions that

- 15 i) more than 20 % by weight of the matrix remain undissolved
on further heating to 112°C or
- ii) more than 8 % by weight of the matrix remain undissolved on
further heating to 117°C or
- 20 iii) more than 1 % by weight of the matrix remain undissolved on
further heating to 122°C

25 are fulfilled by the matrix which remains undissolved on heating
the cooled propylene polymer solution to 80°C.

The present invention furthermore relates to a process for the
preparation of the propylene polymers, their use for the
30 production of films, fibers or moldings and films, fibers or
moldings comprising these propylene polymers.

The unpublished German patent application P 197 10 761.3
describes propylene homopolymers which have particularly high
35 crystallinity and are prepared using a catalyst system containing
a titanium-containing solid component, an aluminum compound and
an electron donor compound.

40 Propylene/ethylene copolymers obtainable by polymerization over
Ziegler-Natta catalysts have been described in many patents.
US-A 4 260 710 discloses the preparation of homo- and copolymers
of alk-1-enes by polymerization with the aid of Ziegler-Natta
catalysts in a stirred kettle. The catalyst components used
contain, inter alia, compounds of polyvalent titanium, aluminum
45 halides and/or alkylaluminum as well as electron donor compounds,
silanes, esters, ethers, ketones or lactones generally being used

00007355-051500

(EP-B 14 523, EP-B 45 977, EP-B 86 473, US-A 857 613, EP-A 171 200).

Furthermore, a number of processes for the preparation of
5 propylene/ethylene block copolymers with the aid of a
Ziegler-Natta catalyst system are known (US-A 4 454 299,
US-A 4 455 405, ZA-B 0084/3561, ZA-B 0084/3563, ZA-B 0084/5261,
GB-B 1 032 945, DE-A 38 27 565), in which first gaseous propylene
10 is polymerized in a first reaction zone and the homopolymer
obtainable therefrom is then brought into a second reaction zone
where a mixture of ethylene and propylene is polymerized thereon.
The process is usually carried out at superatmospheric pressure
and in the presence of hydrogen as a molecular weight regulator.
The copolymers obtainable generally have good impact strength and
15 rigidity.

By varying the amount of the homopolymer obtained in the first
stage and of the copolymer to be polymerized on in the second
20 stage, it is possible to control the impact strength of the
propylene/ethylene block copolymers. However, inevitably a
decrease in the rigidity is associated with an increase in the
impact strength and, conversely, a decrease in the impact
strength with an increase in the rigidity. For some applications
25 of plastics, however, it is necessary to increase the rigidity
without reducing the impact strength or to improve the impact
strength without reducing the rigidity. Moreover, the polymers
should have a very low chlorine content and, for economic
reasons, a further increase in the productivity of the catalyst
30 system used is of interest.

It is an object of the present invention to provide propylene
polymers which have a further improved ratio of rigidity to
toughness, possess a low chlorine content and furthermore can be
35 prepared by a process with increased productivity.

We have found that this object is achieved by the propylene
polymers defined at the outset and a process for their
preparation, their use for the production of films, fibers or
40 moldings and the films, fibers or moldings comprising these
propylene polymers.

The novel propylene polymers are generally present in a form
comprising at least two phases. They contain a continuous phase
45 of a propylene homopolymer, which is referred to as the matrix.
This matrix phase is semicrystalline, ie. it consists of a
crystallized fraction, ie. the crystallites, and an amorphous

8859790-9926055

3

fraction. According to the invention, the term propylene homopolymer is also intended to mean those propylene polymers in which minor amounts of other alkenes are copolymerized units, the propylene homopolymers generally containing less than 2, in particular less than 1, % by weight of other alkenes. The matrix of the novel propylene homopolymers preferably contains only propylene as a monomer.

The novel propylene polymers preferably contain from 50 to 92 % by weight of the matrix-forming propylene homopolymer. Particularly preferably, the amount of the matrix is from 60 to 90 % by weight.

Furthermore, the novel propylene polymers contain a copolymer of propylene and other alkenes, which is present as a separate phase from the matrix and exhibits very low or no crystallinity. This copolymer referred to as a rubber or elastomer contains, as a rule, from 20 to 85 % by weight of propylene. The propylene content of the copolymer is preferably from 35 to 80, in particular from 45 to 70, % by weight. Depending on the chosen ratio of matrix to elastomer, the phase of the copolymer of propylene and other alkenes is present in disperse form in the matrix or is likewise continuous and hence cocontinuous with the matrix.

The other alkenes which are copolymerized with propylene are to be understood as meaning preferably alk-1-enes of up to 10 carbon atoms. Ethylene, but-1-ene, pent-1-ene, hex-1-ene, hept-1-ene and oct-1-ene or mixtures of these comonomers are particularly suitable, ethylene and but-1-ene being preferred. In the case of the copolymers acting as elastomers, unconjugated dienes, such as ethylenenorbornene, dicyclopentadiene or 1,4-hexadiene, may also be present as other alkenes and are then copolymerized, as a rule, with ethylene and propylene.

The novel propylene polymers preferably contain from 8 to 50 % by weight of the copolymer of propylene and other alkenes. Particularly preferably, the amount of the elastomer phase is from 10 to 40 % by weight.

In addition to the essential components, the novel propylene polymers may also contain further homo- or copolymers of alkenes, for example homo- or copolymers of ethylene or polyisobutylene. For example, the amount of the further homo- or copolymers of

alkenes may be from 0 to 30 % by weight, based on the total propylene polymer.

One method for analyzing propylene polymers with regard to the fractions of polymer chains of different tacticity and different comonomer incorporation is TREF (Temperature Rising Elution Fractionation), in which the dissolution temperature of the polymer fraction corresponds to its average length of sequences built up without defects. To carry out the TREF, the propylene polymers are first dissolved in hot, preferably boiling xylene, the solution is then cooled at a constant cooling rate and thereafter the propylene polymers are separated, with increasing temperature, into fractions of different crystallinity. The composition of the propylene polymers can be described in terms of the fraction which remains undissolved on heating the cooled propylene polymer solution to a defined temperature.

In the fractionation of mixtures of propylene homopolymers and copolymers of the propylene with other alkenes, the polymer chains composed of different monomers first go into solution with increasing dissolution temperature, the dissolution temperature being lower the shorter the average sequence lengths of a monomer type. This means that first the elastomer fraction goes into solution and then, at higher temperatures, the matrix, which can be separated again with regard to the average isotactic sequence length of the polymer chains. It has been found that the polymer fractions which go into solution up to and including 80°C can be assigned to the elastomer phase, whereas the fraction which remains undissolved at 80°C and goes into solution only at higher temperatures originates from the matrix.

The novel propylene polymers have a high content of polymer chains with long defect-free isotactic propylene sequences in the matrix. Regarding the matrix, ie. that fraction of the propylene polymers which remains undissolved on heating the cooled polymer solution to 80°C, the propylene polymers fulfill either one or preferably two or all of the following conditions i) to iii):

- i) More than 20, preferably more than 30, in particular more than 40, % by weight of the matrix remain undissolved on further heating to 112°C.
- ii) More than 8, preferably more than 12, in particular more than 16, % by weight of the matrix remain undissolved on further heating to 117°C.

5

iii) More than 1, preferably more than 2, in particular more than 3, % by weight of the matrix remain undissolved on further heating to 122°C.

- 5 To determine according to the invention the composition of the propylene polymers, TREF is carried out in the following manner:

- 1 - 10 g of the propylene polymer are dissolved in a sufficient amount of boiling xylene to give a 0.5-2 % strength by weight solution. The boiling solution is then cooled with a linear cooling rate of from 2 to 15, preferably from 10 to 25, °C/h, or a lower temperature, the major part of the polymer being precipitated. The crystal suspension is then transferred to a thermostatable extraction apparatus which corresponds to that described by W. Holtup in Makromol. Chem. 178 (1977), 2355, and is heated to the first elution temperature. The polypropylene crystals are then extracted for at least 10 minutes at this temperature with vigorous mixing. Thereafter, the polymer solution is discharged while the polymer crystals remain behind in the extractor. The dissolved polymer is precipitated in cold acetone (temperature < 0°C), and the precipitate is filtered off and dried under reduced pressure until the weight is constant.
- 25 The extractor is then heated to the next elution temperature, and xylene at the same temperature is added in the same amount as that used for dissolution. Extraction is then carried out once again for at least 10 minutes with vigorous mixing, the polymer solution is discharged, the dissolved polymer is precipitated in cold acetone and the precipitate is filtered off and dried. These steps are repeated until the total polymer has dissolved.

- The elastomer fraction corresponds to the fractions dissolved up to and including 80°C, and the matrix fraction is the sum of all fractions which dissolve at higher elution temperatures. The matrix fraction insoluble at the individual temperatures is obtained from the ratio of the TREF fraction at the corresponding temperature of the total matrix fraction.

- 40 Since the matrix accounts for only a part of the novel propylene polymers, the fractions which remain undissolved on heating to 112°C, 117°C and 122°C are, based on the total propylene polymer, naturally smaller and are dependent on the ratio of matrix fraction to elastomer fraction.

45

6

The novel propylene polymers can be prepared by mixing the melts of the fractions separately polymerized beforehand. Mixing is then effected in a manner known per se, for example by means of an extruder. The polymer blends prepared in such a manner may also contain polymers which are obtainable with other catalyst systems suitable for the preparation of the matrix, for example polyisobutylenes or ethylene/propylene/diene/(EPDM) rubbers.

However, the novel propylene polymers are preferably prepared in a multistage polymerization process, as a rule the matrix being polymerized in a first stage and a copolymer of propylene with other alkenes then being polymerized thereon in a second stage. In addition, it is possible in subsequent stages to polymerize on further homo- or copolymers of alkenes. Particularly suitable alkenes for such processes are alk-1-enes of up to 10 carbon atoms.

In the process likewise according to the invention, the propylene polymers are prepared by polymerization of propylene at from 50 to 120°C and from 15 to 40 bar in a first polymerization stage and subsequent copolymerization of propylene and other alk-1-enes of up to 10 carbon atoms at from 30 to 100°C and from 5 to 40 bar in a second polymerization stage in the presence of a Ziegler-Natta catalyst system which contains, as active components, a titanium-containing solid component a) which is obtained by reacting a titanium halide with a chlorine-free compound of magnesium, an inorganic oxide as carrier, a C₁-C₈-alkanol and an electron donor compound and, as cocatalysts, an aluminum compound b) and a further electron donor compound c).

For the preparation of the titanium-containing solid component a), the titanium halides used are the halides of trivalent or tetravalent titanium, for example TiBr₃, TiBr₄, TiCl₃ or TiCl₄, or alkoxytitanium halides, such as Ti(OCH₃)Cl₃, Ti(OC₂H₅)Cl₃, Ti(O-iso-C₃H₇)Cl₃, Ti(O-n-C₄H₉)Cl₃, Ti(OC₂H₅)Br₃, Ti(O-n-C₄H₉)Br₃, Ti(OCH₃)₂Cl₂, Ti(OC₂H₅)₂Cl₂, Ti(O-n-C₄H₉)₂Cl₂, Ti(OC₂H₅)₂Br₂, Ti(OCH₃)₃Cl, Ti(OC₂H₅)₃Cl, Ti(O-n-C₄H₉)₃Cl or Ti(OC₂H₅)₃Br, the titanium halides which contain only halogen in addition to titanium and among these in particular the titanium chlorides and especially titanium tetrachloride, being preferred. According to the invention, the titanium halides may also be used as mixtures of one another or in mixtures with further titanium compounds. Examples of suitable further titanium compounds are titanium alcoholates, such as Ti(OCH₃)₄, Ti(OC₂H₅)₄ or Ti(O-n-C₄H₉)₄. Preferably, the titanium halides are used alone.

- Furthermore, a chlorine-free compound of magnesium or a mixture of said compounds is used in the preparation of the titanium-containing solid component. Chlorine-free compounds of magnesium are to be understood according to the invention as meaning those which contain no halogen in their structural formula. However, the amounts of halogen contained as impurities in the novel chlorine-free compounds of magnesium should not exceed 5, in particular 2, % by weight. Suitable chlorine-free compounds of magnesium are in particular alkylmagnesiums and arylmagnesiums as well as alkoxymagnesium and aryloxymagnesium compounds, di-C₁-C₁₀-alkylmagnesium compounds preferably being used. Examples of novel chlorine-free compounds of magnesium are diethylmagnesium, di-n-propylmagnesium, di-isopropylmagnesium, di-n-butylmagnesium, di-sec-butylmagnesium, di-tert-butylmagnesium, diamylmagnesium, n-butylethylmagnesium, n-butyl-sec-butylmagnesium, n-butyloctylmagnesium, diphenylmagnesium, diethoxymagnesium, di-n-propyloxymagnesium, di-isopropyloxymagnesium, di-n-butyloxymagnesium, di-sec-butyloxymagnesium, di-tert-butyloxymagnesium, diamyloxymagnesium, n-butyloxyethoxymagnesium, n-butyloxy-sec-butyloxymagnesium, n-butyloxyoctyloxymagnesium and diphenoxymagnesium. Among these, n-butylethylmagnesium and n-butyloctylmagnesium are particularly preferred.
- In addition, the titanium-containing solid component a) contains at least one inorganic oxide as carrier. As a rule, a finely divided inorganic oxide which has a median particle diameter from 5 to 200 μm , preferably from 15 to 100 μm and in particular from 20 to 70 μm , is used as carrier. The median particle diameter is to be understood here as meaning the volume-related median value of the particle size distribution determined by Coulter Counter Analysis according to ASTM Standard D 4438.
- Preferably, the particles of the finely divided inorganic oxide are composed of primary particles which have a median diameter of the primary particles of from 1 to 20 μm , in particular from 3 to 10 μm . The primary particles are porous, granular oxide particles which in general are obtained by milling a hydrogel of the inorganic oxide. It is also possible to sieve the primary particles before their further processing.

Furthermore, the inorganic oxide preferably to be used is also characterized by the fact that it has cavities or channels with an average diameter of from 0.1 to 20 μm , in particular from 1 to

15 μm , whose macroscopic volume fraction is from 5 to 30 %, in particular from 10 to 30 %, based on the total particle.

The median diameter of the primary particles and the macroscopic volume fraction of the cavities and channels of the inorganic oxide are advantageously determined by image analysis with the aid of scanning electron microscopy or electron probe microanalysis, in each case on particle surfaces and on particle cross-sections of the inorganic oxide. The electron micrographs obtained are evaluated and the median diameter of the primary particles and the macroscopic volume fraction of the cavities and channels are determined therefrom. The image analysis is preferably carried out by conversion of the electron microscopy data into a gray scale binary image and digital evaluation by means of a suitable computer program.

The inorganic oxide preferably to be used may be retained, for example, by spray-drying the milled hydrogel, which is mixed with water or an aliphatic alcohol for this purpose. Such finely divided inorganic oxides are also commercially available.

25 Finely divided inorganic oxide further usually has a pore volume of from 0.1 to 10, preferably 1.0 to 4.0, cm³/g and a specific surface area of from 10 to 1000, preferably from 100 to 500, m²/g, these being understood as the values determined by mercury porosymmetry according to DIN 66133 and by nitrogen adsorption according to DIN 66131.

30 The pH of the inorganic oxide, ie. the negative logarithm to the base 10 of the proton concentration, is preferably from 1 to 6.5, in particular from 2 to 6, particularly preferably from 3.5 to 5.5.

35 Particularly suitable inorganic oxides are the oxides of silicon,
of aluminum, of titanium or of one of the metals of main groups I
and II of the Periodic Table. Silica (silica gel) is a very
preferably used oxide in addition to alumina or magnesium oxide
or a sheet silicate. Mixed oxides, such as aluminum silicates or
40 magnesium silicates, may also be used.

The inorganic oxides used as carrier contain hydroxyl groups on their surface. By elimination of water, it is possible to reduce or completely eliminate the content of OH groups. This can be achieved by thermal or chemical treatment. Thermal treatment is usually carried out by heating the inorganic oxide for from 1 to 24, preferably from 2 to 20, in particular from 3 to 12, hours to

[illegible]

250 to 900°C, preferably 600 to 800°C. The hydroxyl groups may also be removed by chemical methods, by treating the inorganic oxides with conventional drying agents, such as SiCl_4 , chlorosilanes or alkylaluminums. Preferably used inorganic oxides contain from 0.5 to 5 % by weight of water. The water content is conventionally determined by drying the inorganic oxide at 160 °C under atmospheric pressure until the weight is constant. The weight decrease corresponds to the original water content.


10 In the preparation of the titanium-containing solid component a), preferably from 0.1 to 1.0, in particular from 0.2 to 0.5, mol of the chlorine-free compound of magnesium is used per mole of the inorganic oxide.

15 Furthermore, C_1 - C_8 alkanols, such as methanol, ethanol, n-propanol, isopropanol, n-butanol, sec-butanol, tert-butanol, isobutanol, n-hexanol, n-heptanol, n-octanol or 2-ethylhexanol or mixtures thereof, are used in the preparation of the titanium-containing solid component a). Ethanol is preferably
20 used.

The titanium-containing solid component a) furthermore contains electron donor compounds, for example mono- or polyfunctional
25 carboxylic acids, carboxylic anhydrides or carboxylic esters, as well as ketones, ethers, alcohols, lactones or organophosphorus or organosilicon compounds.

Preferably used electron donor compounds within the
30 titanium-containing solid component are carboxylic acid derivatives and in particular phthalic acid derivatives of the formula (II)

35



(II)

40

where X and Y are each chlorine, bromine or C_1 - C_{10} -alkoxy or together are oxygen in an anhydride function. Particularly preferred electron donor compounds are phthalic esters, X and Y being C_1 - C_8 -alkoxy, for example methoxy, ethoxy, n-propyloxy, isopropyloxy, n-butyloxy, sec-butyloxy, isobutyloxy or
45 tert-butyloxy. Examples of preferably used phthalic esters are diethyl phthalate, di-n-butyl phthalate, di-isobutyl phthalate,

dipentyl phthalate, dihexyl phthalate, di-n-heptyl phthalate, di-n-octyl phthalate and di-2-ethylhexyl phthalate.

Other preferred electron donor compounds within the titanium-containing solid component are diesters of 3- or 4-membered, unsubstituted or substituted cycloalkyl-1,2-dicarboxylic acids, and monoesters of substituted benzophenone-2-carboxylic acids or substituted benzophenone-2-carboxylic acids. Hydroxy compounds used in these esters are the alkanols usually employed in esterification reactions, for example C₁-C₁₅-alkanols or C₅-C₇-cycloalkanols, which in turn may carry one or more C₁-C₁₀-alkyl groups, and furthermore C₆-C₁₀-phenols.

¹⁵ Mixtures of different electron donor compounds may also be used.

The titanium-containing solid component a) can be prepared by methods known per se which are described, for example, in EP-A 171 200, GB-A 2 111 066, US-A 48 57 613 and US-A 52 88 824. However, in the first stage of its preparation, the chlorine-free compound of magnesium in an inert solvent is used and is reacted with the carrier and C₁-C₈-alkanol to give a chlorine-free intermediate which is advantageously further processed without purification or extraction.

In the preparation of the titanium-containing solid component a), the following two-stage process is preferably used:

30 In the first stage, a solution of the chlorine-free compound of magnesium is first added to the inorganic oxide in an inert solvent, preferably a liquid alkane or an aromatic hydrocarbon, eg. toluene or ethylbenzene, after which this mixture is allowed to react for from 0.5 to 5 hours at from 10 to 120°C, as a rule
35 with stirring. The C₁-C₈-alkanol is then added in at least a 1.3-fold, preferably from 1.6- to 3-fold, in particular from 1.8- to 2.0-fold, molar excess, based on the magnesium-containing compound, usually with continuous stirring at from -20 to 80°C, preferably from 0 to 40°C. This results in the formation of a
40 chlorine-free intermediate, which is preferably further processed without purification or extraction. After from about 10 to 120, preferably from about 20 to 60, minutes, the titanium halide and the electron donor compound are added to this intermediate at from 10 to 50°C. From 1 to 15, preferably 2 to 5, mol of the
45 titanium halide and from 0.01 to 1, in particular from 0.3 to 0.7, mol of the electron donor compound are used per mole of magnesium of the solid obtained from the first stage. This

11


mixture is allowed to react for at least 10, preferably 30, in particular from 45 to 90, minutes at from 10 to 150°C, in particular from 60 to 130°C, in general with stirring, and the solid substance thus obtained is then filtered off and washed 5 with a C₇-C₁₀-alkylbenzene, preferably with ethylbenzene.

In the second stage, the solid obtained from the first stage is extracted at from 100 to 150°C with excess titanium tetrachloride or with a solution of titanium tetrachloride in an inert solvent, 10 preferably a C₇-C₁₀-alkylbenzene, which solution is present in excess, the solvent containing at least 5 % by weight of titanium tetrachloride. The extraction is carried out as a rule for at least 30 minutes. The product is then washed with a liquid alkane until the titanium tetrachloride content of the wash liquid is 15 less than 2 % by weight.

The titanium-containing solid component a) obtainable in this manner is used with cocatalysts as the Ziegler-Natta catalyst 20 system. Suitable cocatalysts are aluminum compounds b) and further electron donor compounds c).

Examples of suitable aluminum compounds b) are trialkylaluminum, and those compounds in which an alkyl group has been replaced by 25 an alkoxy group or by a halogen atom, for example by chlorine or bromine. The alkyl groups may be identical or different. Linear or branched alkyl groups are suitable. Preferably used trialkylaluminum compounds are those whose alkyl groups are each of 1 to 8 carbon atoms, for example trimethylaluminum, 30 triethylaluminum, triisobutylaluminum, trioctylaluminum or methyldiethylaluminum or mixtures thereof.

In addition to the aluminum compound b), electron donor compounds c), for example mono- or polyfunctional carboxylic acids, 35 carboxylic anhydrides and carboxylic esters, as well as ketones, ethers, alcohols, lactones and organophosphorus and organosilicon compounds are used as the further cocatalyst, it being possible for the electron donor compounds c) to be identical to or different from the electron donor compounds used for the 40 preparation of the titanium-containing solid component a). Preferred electron donor compounds are organosilicon compounds of the formula (I)



(I)

where the radicals R¹ are identical or different and are each C₁-C₂₀-alkyl, 5- to 7-membered cycloalkyl which in turn may be substituted by C₁-C₁₀-alkyl, C₆-C₁₈-aryl or C₆-C₁₈-aryl-C₁-C₁₀-alkyl, the radicals R² are identical or different and are each C₁-C₂₀-alkyl and n is the integer 1, 2 or 3. Particularly preferred compounds are those in which R¹ is C₁-C₈-alkyl or 5- to 7-membered cycloalkyl, R² is C₁-C₄-alkyl and n is 1 or 2.

Among these compounds, dimethoxydiisopropylsilane
10 dimethoxyisobutylisopropylsilane, dimethoxydiisobutylsilane,
dimethoxydicyclopentylsilane, dimethoxydicyclohexylsilane,
dimethoxycyclohexylmethylsilane,
dimethoxyisopropyl-tert-butylsilane,
dimethoxyisobutyl-sec-butylsilane and
15 dimethoxyisopropyl-sec-butylsilane are particularly noteworthy.

The compounds b) and c) acting as cocatalysts may be allowed to act individually, in succession in any desired order or together as a mixture on the titanium-containing solid component a). This is usually effected at from 0 to 150°C, in particular from 20 to 90°C, and from 1 to 100, in particular from 1 to 40 bar.

25 The cocatalysts b) are preferably used in such an amount that the atomic ratio of aluminum from the aluminum compound b) to titanium from the titanium-containing solid component a) is from 10:1 to 800:1, in particular from 20:1 to 200:1.

In the process leading to the novel propylene polymers and like-
wise according to the invention, the molar ratio of the aluminum
compound b) to the further electron donor compound c) is adjusted
to from 1.5:1 to 9:1, in particular 2:1 to 8:1. If a molar ratio
greater than 9:1 is used, the stereospecificity of the resulting
propylene homopolymers is in general insufficient. If the ratio
is less than 1.5:1, the process is generally not very
advantageous for economic reasons, in particular owing to the
large amounts of further electron donor compound c) then used.

Said process can be carried out in the conventional reactors used for the polymerization of C₂-C₁₀-alk-1-enes, either batchwise or, preferably, continuously, inter alia in solution, as suspension polymerization or, preferably, as gas-phase polymerization. Suitable reactors include continuously operated stirred reactors, loop reactors or fluidized-bed reactors. If a batchwise procedure is used, polymerization is effected in the stages in succession by varying the reaction conditions. As a rule, however, the continuous procedure is used, the matrix initially being prepared

Table 1. Demographic characteristics of the study population

Characteristic	Number	Percentage
Age (years)		
< 18	10	1.0
18-24	10	1.0
25-34	10	1.0
35-44	10	1.0
45-54	10	1.0
55-64	10	1.0
65-74	10	1.0
75-84	10	1.0
85-94	10	1.0
≥ 95	10	1.0
Gender		
Male	10	1.0
Female	10	1.0
Ethnicity		
White	10	1.0
Black	10	1.0
Hispanic	10	1.0
Asian	10	1.0
Other	10	1.0
Marital status		
Married	10	1.0
Single	10	1.0
Divorced	10	1.0
Widowed	10	1.0
Education level		
High school or less	10	1.0
Some college	10	1.0
Bachelor's degree	10	1.0
Master's degree	10	1.0
Doctorate	10	1.0
Income (USD)		
< 10,000	10	1.0
10,000-19,999	10	1.0
20,000-29,999	10	1.0
30,000-39,999	10	1.0
40,000-49,999	10	1.0
50,000-59,999	10	1.0
60,000-69,999	10	1.0
70,000-79,999	10	1.0
80,000-89,999	10	1.0
90,000-99,999	10	1.0
≥ 100,000	10	1.0

13

in the first stage in one or more reactors and then the elastomer phase being prepared in one or more further reactors. In addition, it is possible to polymerize on further homo- or copolymers of C₂-C₁₀-alk-1-enes in subsequent stages. It is also possible to combine different reactor types. In a particularly preferred embodiment, the preparation of the copolymers is carried out in a multistage, in particular two-stage, gas-phase process, the reactors used being continuously operated stirred kettles which contain a fixed bed of finely divided polymer which is usually kept in motion by suitable stirring apparatuses.

Said process is carried out by polymerizing propylene or a monomer mixture comprising propylene and minor amounts of other alk-1-enes of up to 10 carbon atoms at from 50 to 120°C, preferably from 60 to 90°C, and from 15 to 40, preferably from 20 to 35, bar for the preparation of the matrix in the first polymerization stage. The average residence time is as a rule from 1.0 to 3.0, preferably from 0.5 to 5, hours. The reaction conditions are preferably chosen so that, in the first polymerization stage, from 0.05 to 2, preferably from 0.1 to 1.5 kg of the matrix are formed per mole of the aluminum component b). Polymerization is usually carried out in the presence of hydrogen, a partial pressure ratio of propylene to hydrogen of, preferably, from 30:1 to 180:1, in particular from 30:1 to 150:1, being established.

The propylene polymer obtained is discharged together with the catalyst from the first polymerization stage and is introduced into the second polymerization stage, where a copolymer of propylene and other alk-1-enes of up to 10 carbon atoms is polymerized onto said propylene polymer. The amount of added monomers is as a rule such that the ratio of the partial pressure of propylene to that of the other alk-1-enes of up to 10 carbon atoms is from 0.5:1 to 20:1, in particular from 1.0:1 to 10:1. Moreover, by a suitable choice of the reaction parameters, the weight ratio of the monomers reacted in the first polymerization stage to those reacted in the second polymerization stage is usually established to be from 0.5 : 1 to 20:1, in particular from 1.0:1 to 15:1.

The polymerization is effected in the second polymerization stage at from 30 to 100°C, preferably from 50 to 90°C, and from 5 to 40, preferably from 10 to 35, bar. The average residence time of the reaction mixture is as a rule from 0.5 to 5, preferably 1.0 to 3.0, hours. The pressure in the second polymerization stage is preferably at least 3 bar below the pressure of the first

14

polymerization stage. In the second polymerization stage, too, the polymerization is preferably carried out in the presence of hydrogen, the ratio of the partial pressure of propylene to that of hydrogen being as a rule from 100:1 to 5:1, in particular from 5 60:1 to 10:1.

It may also be advisable to add a C₁-C₈-alkanol, in particular a C₁-C₄-alkanol, to the reaction mixture of the second polymerization stage, which alkanol influences the activity of
10 the Ziegler-Natta catalyst. Alkanols suitable for this purpose are, for example, methanol, ethanol, n-propanol, n-butanol and very particularly isopropanol. The amount of C₁-C₈-alkanol is in general such that the molar ratio of the C₁-C₈-alkanol to the aluminum compound b) serving as cocatalyst is from 0.01:1 to
15 10:1, in particular from 0.02:1 to 5:1.

The weight average molar masses of the novel copolymers of propylene are as a rule from 10,000 to 1,000,000 g/mol and the
20 melt flow rates (MFR) are from 0.1 to 100, preferably from 0.2 to 20, g/10 min. The melt flow rate (MFR) corresponds to the amount of polymer which is forced, in the course of 10 minutes at 230°C and under a weight of 2.16 kg, out of the test apparatus standardized according to ISO 1133.

25 Compared with the propylene polymers known to date, the novel propylene polymers have a higher proportion of polymer chains with long defect-free isotactic polymer sequences in the matrix. This manifests itself, for example, in an improved ratio of
30 rigidity to toughness. Moreover, the novel copolymers also have reduced chlorine contents. The productivity of the process used for the preparation of these copolymers is substantially higher compared with the known processes.

35 Owing to their good mechanical properties, the novel propylene polymers are particularly suitable for the production of films, fibers or moldings.

40

45

5

According to ISO Standard 1873-1:1991.

Determination of the DSC melting point:

15

20

25

The productivity is the amount of polymer in grams which was obtained per gram of titanium-containing solid component a) used.

Fractionation by crystallinity:

The separation of the propylene polymer with respect to the crystallinity was carried out by preparative fractionation by Temperature Rising Elution Fractionation (TREF). For this purpose, 5 g of each of the propylene polymers were dissolved in 400 ml of boiling xylene and the solution was then cooled linearly to 25°C at a cooling rate of 10°C/h, the major part of the polymer being precipitated.

35

The crystal suspension was transferred to a thermostatable 500 ml extraction apparatus, which corresponds to that described by W. Holtup in Makromol. Chem. 178, (1977) 2335, and was heated to the first elution temperature. The polypropylene crystals were extracted at this temperature for 15 minutes with vigorous mixing. Thereafter, the polymer solution was discharged while the polymer crystals remained behind in the extractor. The dissolved polymer was precipitated in cold acetone (temperature $< 0^{\circ}\text{C}$) and the

45

precipitated in cold acetone (temperature $< 0^{\circ}\text{C}$) and the

16

precipitate was filtered off and dried for from 4 to 5 hours at 100°C under reduced pressure.

5 The extractor was then heated to the next elution temperature and 400 ml of xylene at the same temperature were added. Extraction was carried out once again for 15 minutes with vigorous mixing, the polymer solution was discharged, the dissolved polymer was precipitated in cold acetone and the precipitate was filtered off and dried.

10 These steps were repeated until the total polymer had dissolved. The polymer fractions recovered by precipitating the TREF fractions were in each case from 99.0 to 100 % by weight. To facilitate further calculations, the TREF fractions shown in Table 2 are based on the recovered fractions, ie. the sum of the TREF fractions is 100.0 % by weight.

20 The elastomer fraction corresponds to the amounts dissolved up to and including 80°C and the matrix fraction is the sum of all fractions which have dissolved at higher elution temperatures. The matrix fraction insoluble at individual temperatures is determined from the ratio of the TREF fraction at the corresponding temperature to the total matrix fraction.

Determination of the modulus of elasticity (tensile modulus of elasticity):

30

According to ISO Standard 527-2, at a measuring temperature of 23°C

35 Determination of the notched impact strength:

As Izod notched impact strength according to ISO Standard 180/1A

40 Determination of the chlorine content:

The chlorine content of the polymers was determined by microcoulometric determination according to DIN 51408, Part 2.

45

000970247 0050/48101

17

Determination of the median particle diameter:

- 5 To determine the median particle diameter of the silica gel, the particle size distribution of the silica gel particles was determined by Coulter Counter Analysis according to ASTM Standard D 4438 and the volume-related median value calculated therefrom.

- 10 Determination of the pore volume:

By mercury porosymmetry according to DIN 66133

Determination of the specific surface area:

15

By nitrogen adsorption according to DIN 66131

Determination of the water content:

20

To determine the water content, 5 g of silica gel were dried at 160°C under atmospheric pressure for 15 minutes (weight constancy). The weight decrease corresponds to the original water content.

25

Determination of the macroscopic volume fraction of the cavities and channels:

30

The median particle size of the primary particles and the macroscopic volume fraction of the cavities and channels of the silica gel used were determined with the aid of scanning electron microscopy or electron probe microanalysis, in each case on particle surfaces and particle cross-sections of the silica gel. The electron micrographs obtained were converted into a gray scale binary image and digitally evaluated by means of the software package Analysis from SIS.

35

Example 1

40

Preparation of the titanium-containing solid component a₁)

- 45 In a first stage, a solution of n-butyloctylmagnesium in n-heptane was added to finely divided, spherical silica gel (SiO₂), which had a median particle diameter of 45 µm, a pore volume of 1.5 cm³/g, a specific surface area of 260 m²/g and a water content of 2.7 % by weight, 0.3 mol of the magnesium

18

compound being used per mole of SiO_2 . The finely divided silica gel had a pH of 5.5 and was additionally characterized by a median particle size of the primary particles of 7 μm and by cavities and channels having an average diameter of 5-10 μm , the
5 macroscopic volume fraction of the cavities and channels being about 25 %, based on the total particle. The solution was stirred for 30 minutes at 95°C and then cooled to 20°C, after which the 1.8-fold molar amount, based on the organomagnesium compound, of ethanol was added with cooling, the reaction temperature being
10 kept below 45°C. After 45 minutes, 4.2 mol of titanium tetrachloride and 0.6 mol of di-n-butyl phthalate were added, based in each case on 1 mole of magnesium, to the chlorine-free intermediate without purification or extraction step and with continuous stirring. Thereafter, stirring was carried out for 1
15 hour at 100°C and the solid substance thus obtained was filtered off and washed several times with ethylbenzene.

The solid product obtained therefrom was extracted for 90 minutes in a second stage at 125°C with a 10 % strength by volume solution
20 of titanium tetrachloride in ethylbenzene. Thereafter, the solid product was separated from the extracting agent by filtration and was washed with n-heptane until the extracting agent contained only 0.3 % by weight of titanium tetrachloride.

25 The titanium-containing solid component a_1) thus prepared contained

3.8 % by weight of Ti
7.2 % by weight of Mg
30 28.1 % by weight of Cl.

Polymerization

35 The preparation of the propylene polymers was carried out in a cascade of two vertically stirred gas-phase reactors connected in series and having an effective volume of 200 l each, in the presence of hydrogen as a molecular weight regulator. Both
40 reactors contained an agitated solid bed of finely divided polymer.

Gaseous propylene was passed into the first gas-phase reactor and polymerized continuously under the temperature and pressure
45 conditions shown in Table 1. This was carried out with an average residence time of about 1.5 hours, 1.4 g of the titanium-containing solid component a_1), 90 mmol of

19

triethylaluminum b) and 22.5 mmol of dimethoxydicyclopentylsilane c) being used per hour.

5 The propylene homopolymer obtained after the end of the gas phase
polymerization was then transferred, together with still active
catalyst components, to the second gas-phase reactor. There a
mixture of propylene and ethylene was continuously polymerized
onto this propylene homopolymer under the conditions shown in
10 Table 1 below (pressure, temperature, partial pressure ratio of
propylene to ethylene, weight ratio of converted monomers of the
first stage to converted monomers of the second stage) in the
presence of isopropanol as a regulator.

15 Comparison Example A

Preparation of the titanium-containing solid component a_A)

In a first stage, a solution of n-butyloctylmagnesium in
20 n-heptane was added to the finely divided, spherical silica gel
also used in Example 1, 0.3 mol of the magnesium compound being
used per mole of SiO₂. The solution was stirred for 45 minutes at
95°C and then cooled to 20°C, after which the 10-fold molar
amount, based on the organomagnesium compound, of hydrogen
25 chloride was passed in. After 60 minutes, 3 mol of ethanol per
mole of magnesium were added to the reaction product with
continuous stirring. This mixture was stirred for 0.5 hour at
80°C, after which 7.2 mol of titanium tetrachloride and 0.5 mol of
di-n-butyl phthalate, based in each case on 1 mol of magnesium,
30 were added. Stirring was then carried out for 1 hour at 100°C, and
the solid substance thus obtained was filtered off and washed
several times with ethylbenzene.

The solid product obtained therefrom was extracted for 3 hours at
35 125°C with a 10 % strength by volume solution of titanium
tetrachloride in ethylbenzene. Thereafter, the solid product was
separated from the extracting agent by filtration and was washed
with n-heptane until the extracting agent contained only 0.3 % by
weight of titanium tetrachloride.

40

45

09097865, 061099

20

The titanium-containing solid component a_A) thus prepared contained

- 5 3.5 % by weight of Ti
 7.4 % by weight of Mg
 28.2 % by weight of Cl.

Polymerization

- 10 In a procedure similar to Example 1 according to the invention, a propylene homopolymer was initially prepared in the first reactor, said homopolymer was then transferred to the second reactor and a mixture of propylene and ethylene was polymerized
15 there onto the propylene homopolymer. This was effected under reaction conditions similar to those described in Example 1, except that the titanium-containing solid component a_A) was used. 2.2 g of titanium-containing solid component a_A), 90 mmol of triethylaluminum b) and 22.5 mmol of dimethoxydicyclopentylsilane
20 c) were used per hour.

Examples 2 to 4

- 25 The novel Example 1 was repeated with the same catalyst system, the reaction conditions of pressure, temperature, partial pressure ratio of propylene to ethylene and weight ratio of converted monomers of the first stage to converted monomers of the second stage now being varied according to Table 1.

- 30 Comparative Examples B to D

- The novel Examples 2 to 4 were repeated similarly in each case, except that the titanium-containing solid component a_A) was used
35 in each case.

Table 1 below shows the respective reaction conditions both for the novel Examples 1 to 4 and for the Comparative Examples A to D.

- 40 Table 2 shows, for the novel Examples 1 to 4 and the Comparative Examples A to D, the following properties of the homopolymer matrix, determined after the first polymerization stage: xylene-soluble fraction, melting point and productivity.
45

In addition, Table 2 contains the proportions of the TREF fractions determined for the end product, and the elastomer and matrix contents calculated therefrom as well as the xylene-insoluble fractions, based on the total polymer and on the 5 matrix. The melt flow rate (MFR) of the end product, the rigidity (tensile modulus of elasticity), the Izod notched impact strengths at -20°C and -40°C and the chlorine content of the polymer are also shown.

45

Table 1

	Example 1	Comp. Ex. A	Example 2	Comp. Ex. B	Example 3	Comp. Ex. C	Example 4	Comp. Ex. D
Polymerization stage 1:								
Pressure [bar]	30	30	32	32	32	32	30	30
Temperature [°C]	80	80	80	80	80	80	80	80
Molar ratio aluminum compound b)/ electron donor c)	4 : 1	4 : 1	4 : 1	4 : 1	4 : 1	4 : 1	4 : 1	4 : 1
Polymerization stage 2:								
Pressure [bar]	20	20	20	20	23	23	20	20
Temperature [°C]	70	70	70	70	70	70	70	70
Partial pressure ratio propylene : ethylene	2.0	1.8	2.1	1.9	2.5	2.27	2.5	2.3
Weight ratio converted monomers of 1st stage : converted monomers of 2nd stage	9.0	9.2	5.9	5.8	4.0	3.8	2.3	2.3
Addition of isopropanol [mmol/h]	320	252	224	155	150	104	74	50

BASF AG 5906060

Table 2

	Example 1	Comp. Ex. A	Example 2	Comp. Ex. B	Example 3	Comp. Ex. C	Example 4	Comp. Ex. D
Polymerization stage 1:								
Xylene-soluble fraction [% by weight]	0.5	0.9	0.6	0.9	0.6	0.8	0.5	0.8
DSC melting point [°C]	168.1	166.1	167.8	165.9	167.7	166.0	168.1	166.1
Productivity [g of polymer/g of titanium-containing solid component a)]	34,800	21,700	31,200	20,900	30,600	20,100	29,500	20,700
Polymerization stage 2:								
TREF fractions								
upto and incl. 80°C	5.7	6.3	10.2	11.4	15.3	16.4	21.5	22.0
107°C	13.1	24.1	11.3	26.0	13.5	27.0	15.8	24.5
112°C	21.2	52.8	18.9	50.9	24.2	51.9	29.7	48.6
117°C	36.6	9.9	35.7	7.0	29.3	2.9	18.2	3.0
122°C	19.2	6.9	19.2	4.7	14.4	1.8	12.1	1.9
125°C	4.2	-	4.7	-	3.3	-	2.7	-

BASF AG 970247

Table 2 (continued)

	Example 1	Comp. Ex. A	Example 2	Comp. Ex. B	Example 3	Comp. Ex. C	Example 4	Comp. Ex. D
Fraction soluble in xylene at 80°C (= elastomer fraction) [% by wt.]	5.7	6.3	10.2	11.4	15.3	16.4	21.5	22.0
Xylene-insoluble fraction at:								
80°C (= matrix fraction) [% by wt.]	94.3	93.7	89.8	88.6	84.7	83.6	78.5	78.0
107°C [% by wt.]	81.2	69.3	78.5	62.6	71.2	56.6	62.7	53.5
112°C [% by wt.]	60.0	16.8	59.6	11.7	47.0	4.7	33.0	4.9
117°C [% by wt.]	23.4	6.9	23.6	4.7	17.7	1.8	14.8	1.9
122°C [% by wt.]	4.2	-	4.7	-	3.3	-	2.7	-
Proportion of the matrix which is insoluble in xylene at								
107°C [% by wt.]	86.1	74.0	87.4	70.7	84.1	67.7	79.9	68.6
112°C [% by wt.]	63.6	17.9	66.4	13.2	55.5	5.6	42.0	6.3
117°C [% by wt.]	24.8	7.4	26.3	5.3	20.9	2.2	18.9	2.4
122°C [% by wt.]	4.5	-	5.2	-	3.9	-	3.4	-
MFR [g/10 min]	15.0	15.3	1.8	2.0	3.5	3.7	5.1	5.4
Tensile modulus of elasticity [N/mm ²]	1780	1600	1620	1410	1210	1030	1030	900
Notched impact strength at -20°C [kJ/m ²]	2.7	2.5	4.0	3.2	8.4	8.0	10.8	10.2
Notched impact strength at -40°C [kJ/m ²]	0.9	0.7	2.1	1.8	6.6	6.5	8.8	8.5
Chlorine content of the polymer [ppm]	7.5	12.0	8.0	12.0	7.8	11.9	7.6	11.0

BASF AG 398/5069

A comparison of the novel Examples 1 to 4 with the Comparative Examples A to D clearly shows that the novel propylene polymers have a significantly higher content of very highly isotactic fractions. They have a higher rigidity (tensile modulus of elasticity) in combination with a higher notched impact strength, ie. they have an improved ratio of rigidity to toughness. They also have a lower chlorine content.

10

15

20

25

30

35

40

45

0503785, 061698

We claim:

1. A propylene polymer containing a matrix of a propylene
5 homopolymer and a copolymer of propylene and other alkenes,
wherein, during the separation of the propylene polymers
according to tacticity and comonomer distribution of the
polymer chains, by first dissolving the propylene polymers in
10 boiling xylene, then cooling the solution at a cooling rate
of 10°C/h to 25°C and thereafter, increasing the temperature,
separating the propylene polymers into fractions of different
solubility, either one or more of the conditions that
- i) more than 20 % by weight of the matrix remain
15 undissolved on further heating to 112°C or
- ii) more than 8 % by weight of the matrix remain
undissolved on further heating to 117°C or
- 20 iii) more than 1 % by weight of the matrix remain
undissolved on further heating to 122°C
- are fulfilled by the matrix which remains undissolved on
25 heating the cooled propylene polymer solution to 80°C.
2. A propylene polymer as claimed in claim 1, wherein either one
or more of the conditions that
- 30 i) more than 30 % by weight of the matrix remain
undissolved on further heating to 112°C or
- ii) more than 12 % by weight of the matrix remain
35 undissolved on further heating to 117°C or
- iii) more than 2 % by weight of the matrix remain
undissolved on further heating to 122°C
- 40 are fulfilled by the matrix.
3. A process for the preparation of propylene polymers, in which
propylene is polymerized in a first polymerization stage at
from 50 to 120°C and from 15 to 40 bar and then a copolymer
45 of propylene and other alk-1-enes of up to 10 carbon atoms is
polymerized thereon in a second polymerization stage at from
30 to 100°C and from 5 to 40 bar and the polymerization is

27

carried out in the presence of a Ziegler-Natta catalyst system containing, as active components,

- 5 a) a titanium-containing solid component which is obtained by reacting a titanium halide with a chlorine-free compound of magnesium, an inorganic oxide as carrier, a C₁-C₈-alkanol and an electron donor compound by a procedure in which first,
- 10 in a first stage, a solution of the chlorine-free compound of magnesium in an inert solvent is added to the inorganic oxide as carrier, this mixture is allowed to react for from 0.5 to 5 hours at from 10 to 120°C and is
- 15 then reacted, at from -20 to 80°C with continuous mixing, with a C₁-C₈-alkanol in at least a 1.3-fold molar excess, based on the compound of magnesium, to give a chlorine-free intermediate, the titanium halide and the electron donor compound are then added to said
- 20 intermediate, the resulting mixture is allowed to react for at least 10 minutes at from 10 to 150°C and the solid substance thus obtained is then filtered off and washed, and,
- 25 in a second stage, the solid obtained from the first stage is extracted in an inert solvent which contains at least 5 % by weight of titanium tetrachloride and is washed with a liquid alkane,
- 30 and, as cocatalysts,

b) an aluminum compound and

- 35 c) a further electron donor compound,

wherein, in the first polymerization stage, the molar ratio of the aluminum compound b) to the further electron donor compound c) is adjusted to a ratio of from 1.5 : 1 to 9 : 1.

40

4. A process for the preparation of propylene polymers as claimed in claim 3, wherein, in the first polymerization stage, the molar ratio of the aluminum compound b) to the further electron donor compound c) is adjusted to a ratio of
- 45 from 2 : 1 to 8 : 1.

28

5. A process for the preparation of propylene polymers as claimed in claim 3, wherein the titanium-containing solid component a) is prepared using, as carrier, an inorganic oxide which has a pH of from 1 to 6.5, a median particle diameter from 5 to 200 μm and cavities or channels with an average diameter of from 1 to 20 μm , whose macroscopic volume fraction is from 5 to 30 %, based on the total particle.
6. A process for the preparation of propylene polymers as claimed in claim 3, wherein a silica gel is used as the inorganic oxide in the preparation of the titanium-containing solid component a).
7. A process for the preparation of propylene polymers as claimed in claim 3, wherein a trialkylaluminum compound whose alkyl groups are each of 1 to 8 carbon atoms is used as the aluminum compound b).
8. A process for the preparation of propylene polymers as claimed in claims 3, wherein at least one organosilicon compound of the formula (I)



- where the radicals R^1 are identical or different and are each C_1 - C_{20} -alkyl, 5- to 7-membered cycloalkyl which in turn may be substituted by C_1 - C_{10} -alkyl, or C_6 - C_{18} -aryl or C_6 - C_{18} -aryl- C_1 - C_{10} -alkyl, the radicals R^2 are identical or different and are each C_1 - C_{20} -alkyl and n is the integer 1, 2 or 3, is used as a further electron donor compound.
9. A process for the preparation of propylene polymers as claimed in claim 3, wherein the polymerization in the second polymerization stage is carried out in the presence of a C_1 - C_8 -alkanol.
10. A propylene polymer obtainable by a process as claimed in claim 3.
11. A method of use of a propylene polymer as claimed in claim 1 for the production of films, fibers or moldings.
12. A method of use of a propylene polymer as claimed in claim 10 for the production of films, fibers or moldings.

29

13. A film, fiber or molding comprising a propylene polymer as claimed in claim 1.

14. A film, fiber or molding comprising a propylene polymer as
5 claimed in claim 10.

10

15

20

25

30

35

40

45

Propylene polymers

5 Abstract

Propylene polymers containing a matrix of a propylene homopolymer and a copolymer of propylene and other alkenes, wherein, during the separation of the propylene polymers according to tacticity and comonomer distribution of the polymer chains, by first
10 dissolving the propylene polymers in boiling xylene, then cooling the solution at a cooling rate of 10°C/h to 25°C and thereafter, increasing the temperature, separating the propylene polymers into fractions of different solubility, either one or more of the
15 conditions that

- i) more than 20 % by weight of the matrix remain undissolved on further heating to 112°C or
- 20 ii) more than 8 % by weight of the matrix remain undissolved on further heating to 117°C or
- iii) more than 1 % by weight of the matrix remain undissolved on further heating to 122°C

25

are fulfilled by the matrix which remains undissolved on heating the cooled propylene polymer solution to 80°C,

30 a process for the preparation of the propylene polymers, their use for the production of films, fibers or moldings and the films, fibers or moldings comprising these propylene polymers, are described.

35


40

45

05007305, 061503

United States Patent & Trademark Office

Office of Initial Patent Examination -- Scanning Division



Application deficiencies found during scanning:

1. Application papers are not suitable for scanning and are not in compliance with 37 CFR 1.52 because:
 - ☐ All sheets must be the same size and either A4 (21 cm x 29.7 cm) or 8-1/2" x 11". Pages _____ do not meet these requirements.
 - ☐ Papers are not flexible, strong, smooth, non-shiny, durable, and white.
 - ☐ Papers are not typewritten or mechanically printed in permanent ink on one side.
 - ☐ Papers contain improper margins. Each sheet must have a left margin of at least 2.5 cm (1") and top, bottom and right margins of at least 2.0 cm (3/4").
 - ☐ Papers contain hand lettering.
2. Drawings are not in compliance and were not scanned because:
 - ☐ The drawings or copy of drawings are not suitable for electronic reproduction.
 - ☐ All drawings sheets are not the same size. Pages must be either A4 (21 cm x 29.7 cm) or 8-1/2" x 11".
 - ☐ Each sheet must include a top and left margin of at least 2.5 cm (1"), a right margin of at least 1.5 cm (9/16") and a bottom margin of at least 1.0 cm (3/8").
3. Page(s) _____ are not of sufficient clarity, contrast and quality for electronic reproduction.
4. Page(s) _____ are missing.
5. OTHER: NO Declaration / NO Drawings

069733" 59826060